

TEST REPORT

Applicant: MID OCEAN BRANDS BV
7/F, KINGS TOWER,
111 KING LAM STREET,
CHEUNG SHA WAN,
KOWLOON
HK
Attn: DEREK HUI/EMMA LAM

Number: HKGH03055153

Date: Sep 29, 2023

Sample and Information provided by customer :
Item Name : **Sunglasses in RPET**
Item No. : **MO6531**
Quantity : **7 pairs**
Vendor : **115663**
Country of Origin : **China**



For and on behalf of :
Intertek Testing Services HK Ltd.

Cindy I.K. Chan
Vice President



TEST REPORT

Number : HKGH03055153

Conclusion:

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details :

<u>Requirement</u>	<u>Result</u>
(1) BS EN ISO 12312-1:2013+A1:2015 Eye and face protection – Sunglasses and related eyewear – Part 1: Sunglasses for general use, excluding: - Clause 4.3 - Physiological compatibility - Clause 5.3.2.2 - Driving in twilight or at night - Clause 12 - Information and labelling	Pass
(2) UV-400 *****	See details enclosed

Decision Rule(s):

When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to Intertek's "Decision Rule Document" and is available on Intertek's website. <https://intertekhk.grd.by/decision-rule-doc..>
If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Document" is not applicable and indication of "∞" was shown as above table.



TEST REPORT

Number : HKGH03055153

(1) Requirements for Sunglasses (Uniformly Tinted Lenses)

Test standard: BS EN ISO 12312-1:2013+A1:2015 – Eye and face protection – Sunglasses and related eyewear – Part 1: Sunglasses for general use

Test method refers ISO 12311:2013 Personal protective equipment - Test methods for sunglasses and related eyewear.

Number of samples tested: Four (4) pairs

Note :

- (1) The submitted sunglasses were declared by applicant for adult use.
- (2) Physiological compatibility
Note: Sunglasses shall be designed and manufactured in such a way that when used under the conditions and for the purposes intended, they will not compromise the health (and safety) of the wearer. The risks posed by substances leaking from the device that may come into prolonged contact with the skin shall be reduced by the manufacturer to below any regulatory limit. Special attention shall be given to substances which are allergenic, carcinogenic, mutagenic or toxic to reproduction.
- (3) CE marking or UKCA marking is not specified in BS EN ISO 12312-1:2013+A1:2015. However, per Regulation (EU) 2016/425 or UK2019 SI696 Schedule 35 Regulation 38, the CE marking or UKCA marking shall be affixed visibly, legibly and indelibly to the sunglasses frame respectively.

It was found that both CE marking and UKCA marking were provided on the sunglasses frame.

Clause	Requirement	Result
4	Construction and materials	
4.1	Construction	P
4.2	Filter material and surface quality	P
4.3	Physiological compatibility	Note (2)
5	Transmittance	
5.2	Transmittance and filter categories	P
5.3	General transmittance requirements	
5.3.1	Uniformity of luminous transmittance	P
5.3.2.1a	Spectral transmittance	P
5.3.2.1b	Detection of signal lights	P
5.3.2.2	Driving in twilight or at night	#1
5.3.3	Wide angle scattering	P
5.3.4	Additional transmittance requirements for specific filter types	
5.3.4.1	Photochromic filters	NA
5.3.4.2	Polarizing filters	NA
5.3.4.3	Gradient filters	NA
5.3.5	Claimed transmittance properties	NA (No claim)
6	Refractive power	



TEST REPORT

Number : HKGH03055153

Clause	Requirement	Result
6.1	Spherical and astigmatic power	P
6.2	Local variations in refractive power	NA
6.3	Prism imbalance (relative prism error)	P
7	Robustness	
7.1	Minimum robustness of filters	P
7.2	Frame deformation and retention of filters	P
7.3	Impact resistance of the filter, strength level 1 (optional specification)	NA (No claim)
7.4	Increased endurance of sunglasses (optional specification)	NA (No claim)
7.5	Resistance to perspiration (optional specification)	NA (No claim)
7.6	Impact resistance of the filter, strength level 2 or 3 (optional specification)	NA (No claim)
8	Resistance to solar radiation	P
9	Resistance to ignition	P
10	Resistance to abrasion (optional specification)	NA (No claim)
11	Protective requirements	
11.1	Coverage area	P
11.2	Temporal protective requirements	NA
12	Information and labeling	
12.1	Information to be supplied with each pair of sunglasses	#2 (Note 3)
12.2	Additional information	#3

Abbreviation: P = Pass; NA = Not Applicable

Test data:

5.2 Transmittance and filter categories

Range	Left ocular (%)	Right ocular (%)	Filter category
380 - 780nm (Tv)	26.49	26.24	2

Range	Maximum transmittance (%)		Limit (%)	
	Left ocular	Right ocular	Left	Right
280 - 315nm (T _{SUVB})	< 0.10	< 0.10	≤ 0.05Tv (1.32)	≤ 0.05Tv (1.31)
315 - 380nm (T _{SUVA})	< 0.10	< 0.10	≤ 0.5Tv (13.24)	≤ 0.5Tv (13.12)



TEST REPORT

Number : HKGH03055153

Requirement:

Consumer label	Technical label	Requirements		
Descriptive label	Filter category	Ultraviolet spectral range		Visible spectral range
		Maximum value of solar UV-B transmittance T_{SUVB} 280 nm to 315 nm	Maximum value of solar UV-A transmittance T_{SUVA} 315 nm to 380 nm	Range of luminous transmittance (T_v) 380 nm to 780 nm
Light tint sunglasses	0	0.05 T_v	T_v	$T_v > 80\%$
	1	0.05 T_v	T_v	$43\% < T_v \leq 80\%$
General purpose sunglasses	2	1.0% absolute or 0.05 T_v , whichever is greater	0.5 T_v	$18\% < T_v \leq 43\%$
	3	1.0% absolute	0.5 T_v	$8\% < T_v \leq 18\%$
Very dark special purpose sunglasses	4	1.0% absolute	1.0% absolute or 0.25 T_v , whichever is greater	$3\% < T_v \leq 8\%$

5.3.1 Uniformity of luminous transmittance

Uniformity	Left ocular	Right ocular	Limit (%)
% variation within filter [relative to higher value]	5.07	7.95	≤ 10
% difference between filters [relative to lighter filter]	0.95		≤ 15

5.3.2.1a Spectral transmittance

Range	Minimum transmittance (%)		Limit (%)	
	Left ocular	Right ocular	Left ocular	Right ocular
475 - 650nm	24.58	24.18	$\geq 0.2 T_v$ (5.30)	$\geq 0.2 T_v$ (5.25)

5.3.2.1b Detection of signal lights

Signal light	Relative visual attenuation quotient, Q		Limit
	Left ocular	Right ocular	
Red	1.06	1.06	≥ 0.80
Yellow	0.99	0.99	≥ 0.60
Blue	1.06	1.06	≥ 0.60
Green	1.00	1.00	≥ 0.60

5.3.3 Wide angle scattering

Wide angle scattering (%)	Left ocular	Right ocular	Requirement
	0.8	0.7	≤ 3



TEST REPORT

Number : HKGH03055153

6.1 Optical power of oculars mounted in spectacles

Optical power	Left ocular	Right ocular	Limit
Spherical power (m ⁻¹)	-0.07	-0.07	± 0.12
Astigmatic power (m ⁻¹)	0.01	0.01	≤ 0.12
Difference of spherical power between left and right filters (m ⁻¹)	0		≤ 0.18

6.3 Prism imbalance (relative prism error)

Prismatic power difference (cm/m)			Limit (cm/m)
Horizontal	Base out	0.10	≤ 1.00
	Base in	--	≤ 0.25
Vertical		0.025	≤ 0.25

8 Resistance to radiation

(a) Relative change in the luminous transmittance after irradiation

Left ocular (%)	-0.02	Requirement ± 3% for category 0 ± 5% for category 1 ± 8% for category 2 ± 10% for categories 3 & 4
Right ocular (%)	0	

(b) Wide angle scattering after solar radiation

Left ocular (%)	Right ocular (%)	Requirement (%)
0.8	0.7	≤ 3

(c) After the solar radiation process, the submitted sample also met the requirement for the ultraviolet spectral range for Tv as given by table 1 of the standard.

Remarks:

- #1 - The applicant shall provide that the following warning will be printed on the labels, packaging, etc that accompanies the sunglasses at the point of the sale:
- "Not suitable for driving in twilight or at night" or
 - "Not suitable for driving at night or under condition of dull light"



TEST REPORT

Number : HKGH03055153

#2 - The manufacturer shall provide information for the user with each pair of sunglasses. This information shall be in the form of markings on the frame or separate information on labels, packaging, etc., that accompanies the sunglasses at the point of sale.

- a) Identification of model.
- b) Name and address of the manufacturer.
- c) Reference to this part of ISO 12312.
- d) Type of filter, if photochromic and/or polarizing.
- e) Number of the filter category (in both the faded and darkened states for photochromic filters) marked preferably on the frame or on the filter.
- f) Description of the filter category in the form of a symbol and/or verbal description as given in Table 5. and explanation of these symbols. The minimum height of the symbols shall be 5 mm.
- g) Restrictions of use, which shall include at least the following:
 - 1) not for direct observation of the sun;
 - 2) not for protection against artificial light sources e.g. solaria;
 - 3) not for use as eye protection against mechanical impact hazards (for products not satisfying the requirements of 7.3 or 7.6);
 - 4) any other restrictions deemed appropriate to be communicated by the manufacturer, e.g. increased or decreased transmittance of photochromic glasses due to high or low temperatures or to low light conditions.
- h) When the filter does not meet the necessary requirements for driving and for filter category 4, the following warning: "Not suitable for driving and road use" in the form of either of the symbols shown in figure 2 of BS EN ISO 12312-1:2013+A1:2015 and/or in writing. The minimum height of the symbol shall be 5 mm.
- i) If relevant, instructions for care and cleaning if the wrong use of cleaning products might damage the sunglasses and a list of damaging products not suitable for cleaning.

#3 - The following information shall be available from the manufacturer on request.

- a) An explanation of the trademarks that are not universally recognized or foreseen by the users of this part of ISO 12312.
- b) The position of the reference point when different from the one defined in this part of ISO 12312.
- c) The country of origin (e.g. "made in").
- d) The nominal value of luminous transmittance.
- e) Transmission requirements applicable to this product.
- f) Polarization efficiency in cases of polarizing filters.
- g) The base material of filters and frame.

∞ - Decision rule required by the standard

If the measurement result plus or minus the uncertainty of measurement overlap the limit value of the test, the result shall be deemed to be a failure.

Date sample received : Sep 18, 2023

Testing period : Sep 18, 2023 to Sep 27, 2023



Page 7 of 9



TEST REPORT

Number : HKGH03055153

(2) UV-400

Test Method : Assessment was made against a level of 100% UV protection, in which the spectral transmittance was examined within a range of 280nm - 400nm to ensure that a transmittance value of 0.5% was not exceeded.

Number of sample tested : One (1) pair.

Result :

Wavelength (nm)	Transmittance (%)	
	Left ocular	Right ocular
280	<0.10	<0.10
285	<0.10	<0.10
290	<0.10	<0.10
295	<0.10	<0.10
300	<0.10	<0.10
305	<0.10	<0.10
310	<0.10	<0.10
315	<0.10	<0.10
320	<0.10	<0.10
325	<0.10	<0.10
330	<0.10	<0.10
335	<0.10	<0.10
340	0.11	<0.10
345	<0.10	<0.10
350	<0.10	<0.10
355	<0.10	<0.10
360	<0.10	<0.10
365	<0.10	<0.10
370	<0.10	<0.10
375	<0.10	<0.10
380	<0.10	<0.10
385	<0.10	<0.10
390	<0.10	<0.10
395	<0.10	<0.10
400	0.42	0.38



TEST REPORT

Number : HKGH03055153

Comment :The submitted sample was considered acceptable to make a claim of "UV 400" protection, the criteria of which was mentioned above.

Date sample received : Sep 18, 2023
Testing period : Sep 18, 2023 to Sep 27, 2023

End of report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the reports, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

